



Advanced Specialty Polymer

11-16, Daedong-ro 530 Beon-gil, Daeso-myeon, Eumseong-gun, Chungcheongbuk-do, Republic of Korea  
ZIP 27677, TEL : +82-43-882-5091, Fax : +82-43-882-5092

## PRODUCT SPECIFICATION SHEET

ver. 1.0

**Product : Diasphere® MH-80FD**

| Test ID | Test Name              | Min / Max / Text   | Test Method   |
|---------|------------------------|--|---|
| 001A    | Appearance             | Fine White Powder  | Visual  |
| 002A    | Odor                   | None   | Organoleptic  |
| 003A    | Loss on Drying, %      | 0 1  | 2hrs@105°C  |
| 004A    | Mean Particle Size, um | 74 86  | Coulter counter M3  |
| 005A    | pH                     | 6 8  | 2% Dispersion [1g into 50ml<br>(MeOH:H <sub>2</sub> O=1:2)] |
| 006A    | Decomposition Temp, °C | 260  | 3% Weight loss by TGA                                       |
| 001B    | RoHS                   | Not Detected   | Attached SGS RoHS Data                                      |
| 001C    | Note                   | All the ingredients in this Product meet the requirement for that ingredient as specified in 2 CFR |   |

